



Product Data Sheet

Castrol Hyspin AWS Range

Anti-wear hydraulic oil

Description

Castrol Hyspin™ AWS hydraulic oil range is based upon highly refined mineral oil enhanced with a stabilised zinc additive system.

Application

Hyspin AWS has been specially formulated to provide good anti-wear and thermal stability performance using proven additive technology. The careful blend of additives with a high quality base stock ensures that Hyspin AWS has excellent hydrolytic and oxidative stability while exhibiting a minimal tendency to produce sludge and deposits.

Hyspin AWS provides corrosion protection to ferrous and yellow metal components found within a hydraulic system. This range is designed for use in industrial hydraulic systems which require antiwear protection such as lightly loaded gears, variable speed units and bearings. The Hyspin AWS range is compatible with the most commonly used nitrile, silicone and fluoropolymer seal materials.

Hyspin AWS is classified as follows:

DIN 51502 classification - HLP
ISO 6743/4 - Hydraulic Oils Type HM

Hyspin AWS (for appropriate viscosity grade) is approved by:

Parker Hannifin (Denison) HF0, HF1 & HF2
Eaton E-FDGN-TB002-E

Hyspin AWS grades meet the requirements (for appropriate viscosity grade) of:

DIN 51524 Part 2
Fives Cincinnati P68, P69 & P70
ASTM D6158 HM
ISO 11158 HM
US Steel 126
GB 11118.1 L-HM (General and High Pressure)

Advantages

Hyspin AWS has the following advantages when compared to conventional hydraulic oils:

- Good thermal and oxidative stability. Oxidative stability reduces deposit formation, resulting in a cleaner system. This can extend the machinery's operating life.
- Excellent anti-wear performance increases wear protection, which can help reduce downtime caused by unscheduled maintenance.
- Good filterability characteristics, including in the presence of water, enables cost savings to be made from increased filter life and reduced maintenance.
- Excellent water separation and hydrolytic stability, measured by industry standard testing. This increases equipment reliability, helping to prolong the lubricant's life and reduce downtime.

Typical Characteristics

Name	Method	Units	AWS 32	AWS 46	AWS 68	AWS 150
ISO Viscosity Grade	-	-	32	46	68	150
Density @ 15°C / 59°F	ISO 12185 / ASTM D4052	kg/m ³	880	880	880	890
Kinematic Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm ² /s	32	46	68	150
Kinematic Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm ² /s	5.3	6.7	8.6	14.5
Viscosity Index	ISO 2909 / ASTM D2270	-	116	112	103	96
Pour Point	ISO 3016 / ASTM D97	°C/°F	-27/ -17	-24/ -11	-21/ -6	-15/ 5
Foam Sequence I - tendency / stability	ISO 6247 / ASTM D892	ml/ml	10/0	10/0	10/0	10/0
Flash Point - open cup method	ISO 2592 / ASTM D92	°C/°F	210/ 410	215/ 419	225/ 437	230/ 446
Flash Point - closed cup method	ISO 2719 / ASTM D93	°C/°F	200/ 392	200/ 392	220/ 428	220/ 428
Water Separation @ 54°C / 129°F (40/37/3)	ISO 6614 / ASTM D1401	min	15	15	15	-
Water Separation @ 82°C / 180°F (40/37/3)	ISO 6614 / ASTM D1401	min	-	-	-	20
Air Release @ 50°C / 122°F	ISO 9120 / ASTM D3427	min	4	8	8	18
FZG Gear Scuffing test - A/8.3/90	ISO 14635-1	Failure Load Stage	11	12	12	12
Rust test - distilled water (24 hrs)	ISO 7120 / ASTM D665A	-	Pass	Pass	Pass	Pass
Rust test - synthetic seawater (24 hrs)	ISO 7120 / ASTM D665B	-	Pass	Pass	Pass	Pass

Subject to usual manufacturing tolerances.

Castrol Hyspin AWS Range

08 Aug 2024

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Singapore Pte. Limited (202034037D), 7 Straits View, Marina One East Tower, #26-01, Singapore 018936
 Phone No : 800-120-7082
www.castrol.com