

Castrol Braycote 868

Grease, Molybdenum Disulfide and Silicone Oil

Description

Castrol Braycote 868 is a grayish-black homogeneous mixture of molybdenum disulfide and silicone oil.

Application

Castrol Braycote 868 is designed for use on slow-speed sliding surfaces operating at temperatures up to 400°C (752°F) and as an anti-seize compound on threaded parts which operate at temperatures up to 760°C (1400°F).

Typical Characteristics

TEST METHOD	DESCRIPTION	SPECIFICATION REQUIREMENTS	RESULT
-------------	-------------	----------------------------	--------

Base Oil:

D 1500	Color, ASTM	2.0 Maximum	<0.5
D 92	Flash Point, °C (°F)	274 (525) Maximum	300 (572)
D 445	Viscosity		
	@ 100°C (212°F), cSt	16-22	19.5
	@ 40°C (104°F), cSt	65-85	69

Grease:

	Molybdenum Disulfide MIL-M-7866	Must Conform	Pass
--	------------------------------------	--------------	------

Composition Requirement

	Molybdenum Disulfide, % wt	49-51	50
	Silicone Fluid, % wt	49-51	50
D 2595	Evaporation Loss, % wt 22 hrs @ 149°C (300°F)	Report	4.5
D 217	Penetration Worked @ 25°C (77°F), mm ⁻¹		240

Additional Information

Temperature Range

-7°C to 404°C (19°F to 759°F)

Packaging

Castrol Braycote 868 is available in 12/1 pound cases.

Specifications

Castrol Braycote 868 meets the requirements of, but is not qualified to, specification DOD-L-25681D.

Castrol, Braycote, and the Castrol logo are trademarks of Castrol Limited, used under licence

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Limited, Pipers Way, Swindon, Wiltshire SN3 1RE, UK
www.castrol.com/industrial