



Product Data

High Temperature Grease

Multipurpose high temperature grease

Description

High Temperature Grease is a high performance, multipurpose lithium complex grease developed using an optimised combination of high quality mineral oil, proprietary thickener technology and a specially selected additive system enabling reliable performance across a wide range of temperatures whilst exposed to a variety of operational loads, speeds and environmental conditions.

Application

High Temperature Grease is intended for use in a wide range of plain and rolling element bearings within both the Automotive and Industrial markets, especially targeting those applications where upper operating temperatures are likely to exceed the limits of conventional, lithium thickened greases.

The excellent thermal and mechanical stability of High Temperature Grease make it particularly suitable for use in automotive bearing applications where rotational speeds may be higher or prolonged heavy braking may generate higher than normal hub temperatures. Specific examples may include cars fitted with disc brakes or commercial vehicles such as trucks or buses.

High Temperature Grease also offers good resistance to water and corrosion as well as very good load carrying performance making it suitable for general vehicle chassis lubrication or bearings on off-road construction vehicles where greater extremes of pressure may be prevalent.

Advantages

- Excellent thermal and mechanical stability ensure prolonged product integrity across a wider operating temperature range, thus enabling extended relubrication intervals and reduced maintenance.
- Good extreme pressure and anti-wear properties provide the potential for prolonged component life.
- Good water resistance provides enhanced protection in applications where the potential for exposure and contamination are higher.
- Good corrosion protection.
- Excellent multipurpose potential enabling a reduction in product inventory.

Typical Characteristics

Name	Method	Units	High Temperature Grease
Thickener	-	-	Lithium Complex
Base Oil	-	-	Mineral
Appearance	Visual	-	Smooth, Brown & Homogeneous
NLGI Grade	ASTM D 217		2
Cone Penetration, Worked 60 Strokes	IP 50	10ths/mm	275
Cone Penetration, Worked 100,000 Strokes	IP 50	10ths/mm	285
Base Oil Viscosity @ 40°C	ASTM D445	cSt	180
Drop Point	IP 396	°C	260
Oil Separation, 18 hrs @ 100°C	IP 121	%	7.5
Oil Separation	ASTM D 1742	%	3.6
Water Washout, 1 hr @ 79°C	ASTM D 1264	% w t	3.5
Emcor Corrosion Protection, Distilled Water	IP 220	Rating	0 - 0
Corrosion Prevention	ASTM D 1743	Rating	Pass
Pressure Vessel Oxidation, Pressure Drop at 100 hrs	ASTM D 942	psi	2.0
4 Ball Weld Point	IP 239	kg	310
Wheel Bearing Leakage @ 105°C	ASTM D 1263	g	2.3
Temperature Range			-30°C to +140°C

The above figures are typical of those obtained with normal production tolerance and do not constitute a specification.

Storage

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and the obliteration of drum markings. Products should not be stored above 60°C, exposed to hot sun or freezing conditions.

High Temperature Grease

22 Jul 2011

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Marine, Technology Centre, Whitchurch Hill, Pangbourne, Reading RG8 7QR, United Kingdom

www.castrol.com/marine