

Castrol Spheerol SY-HT 2

High temperature grease

Description

Spheerol™ SY-HT 2 is a premium quality, anti-wear grease primarily intended for high temperature applications.

It combines the unique features of synthetic base fluids with an inorganic thickener. The wax free nature of the synthetic base fluid and its low traction coefficient (compared with mineral oils), provides excellent stability against oxidation at high temperatures as well as superior low temperature lubrication. Spheerol SY-HT 2 offers the potential for energy savings through reduced friction, lower torque and reduced temperatures in the load zone of rolling element bearings. The inorganic thickener contributes to excellent structural stability at very high temperatures as well as a high dropping point.

Spheerol SY-HT 2 does not contain lead, chlorine or nitrites.

Application

Spheerol SY-HT 2 is recommended for use in high speed bearings and thrust bearings where a wide temperature range is desired and also in high temperature applications where extended service between relubrication intervals is required. It is particularly suitable for use in electric motor bearings where operating conditions demand reduced friction, low wear and long service life. Spheerol SY-HT 2 has a recommended operating temperature range of -50°C to 200°C, with appropriate re-lubrication intervals.

Advantages

- Reduced downtime and lower maintenance costs due to outstanding high and low temperature performance
- Extended service life with longer intervals between re-lubrication because of excellent resistance to oxidation
- Reduced energy consumption (low coefficient of traction)
- Maintenance of grease structure at high temperatures
- Outstanding low temperature pumpability
- Reduced volatility

Typical Characteristics

	Test Methods	Units	SY HT 2
Thickener type	-	-	Inorganic
NLGI Classification	ISO 2137 / ASTM D 217	-	2
Colour	Visual	-	Brown
Texture	Visual	-	Smooth / Tacky
Dropping Point	ISO 2176 / ASTM D2265	°C	>260 (Non Melting)
Base Oil Viscosity @ 40°C	ISO 3104 / ASTM D445	cSt	100
Worked Penetration, 25°C / 60 Strokes	ISO 2137 / ASTM D217	0.1mm	265-295
Penetration, Worked 100,000 Strokes	ISO 2137 / ASTM D217	0.1mm	60
Copper Corrosion (24h/ 100°C)	ISO 2160 / ASTM D4048		1b
4 - Ball Weld Load	ASTM D 2783 / DIN 51350/4	N	2500
DIN Classification	DIN 51 502		K2N-50

Additional Information

In order to minimise potential incompatibilities when converting to a new grease, all previous lubricant should be removed as much as possible prior to operation. During initial operation, re-lubrication intervals should be monitored closely to ensure all previous lubricant is purged.

Castrol, Spherol, and the Castrol logo are trademarks of Castrol Limited, used under licence

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Limited, Pipers Way, Swindon, Wiltshire SN3 1RE, UK
www.castrol.com/industrial
www.castrol.com/industrial