



Pyroplex Blue

PYROPLEX BLUE GREASE

Description

Castrol Pyroplex Blue is a unique, lithium-complex grease that uses exclusive Hydro-Activation™ technology to maintain mobility while building tack and adhesion in wet conditions and highly humid environments. It is formulated with a proprietary additive package that promotes exceptionally long bearing life when compared with competitive grease products. Castrol Pyroplex Blue delivers almost twice the level of antiwear performance of a typical multipurpose ASTM D3527 Wheel-Bearing Life Test EP grease. In high-temperature environments, film strength is increased between metal surfaces, and the affinity for metal surfaces is enhanced.

Advantages

Industry Specifications and OEM Approvals by Grade

Castrol Pyroplex Blue delivers:

- Multifunctional use for both on and off road.
- Better adhesion with improved mobility.
- Increased tack and adhesion in the presence of water (note water spray-off).
- Enhanced extreme pressure and anti-wear performance (note four ball weld).
- Excellent high temperature performance (note drop point).
- GC-LB approved grease.
- Superior rust and oxidation control.

Castrol Pyroplex Blue's Dependable performance under varying conditions reduces maintenance costs while extending equipment life. Castrol Pyroplex Blue's environmental impact is reduced through the non-utilization of Antimony, Barium, Lead, or Chlorinated Compounds.

Industry Specifications and OEM Approvals by Grade

Exceeds GC-LB (NLGI #1 grade only)

Typical Characteristics

Name	Method	Units	Pyroplex Blue 1	Pyroplex Blue 2
Appearance		-	Smooth-Tacky/ Stringy	Smooth-Tacky/ Stringy
Thickener -Type			Lithium Complex	Lithium Complex
Colour		-	Blue-	Blue
Penetration, worked @77F	ASTM D217	1/10 mm	325	280
Dropping point, F	ASTM D2265	°F	530	550
Four Ball EP Properties, Weld Point (Kg)	ASTM D2596	Kg Load	500	500
Load Wear Index	ASTM D2596	kgf	90	93
Four Ball Wear Scar, mm	ASTM D2266	mm Scar	0.33	0.39
Timken OK Load	ASTM D2509	lb	60	60
Mobility-g/Min. 77F			660	410
Mobility-g/Min. 60F			300	170
Mobility-g/Min.40F			82	55
Mobility-g/Min.20F			27	14
Mobility-g/Min 0F			6	2
Water Spray Off @100F,%	ASTM D4049	% wt	40	18
Base Oil Viscosity,SSU@100F	D445		750	1150
Base Oil Viscosity,SSU@210F	D445		75	115
Base Oil Viscosity,SSU@40C	D445		114	247
Base Oil Viscosity,SSU@100C	D445		60	24
Rust Prevention	D1743		Pass	Pass
Wheel Bearing Life,hrs	D3527		225	240
Wheel Bearing Leakage, g	D4290		9.3	1.9
Oxidation Stability,@ 100 Hr,psi loss	D942		2	1
Copper Corrosion	D4048		1B	1B

Removal

This is what you should do to dispose of the product effectively and safely

Storage

Please store the product in a container out of direct sunlight etc.

Pyroplex Blue

04 Aug 2023

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

BP Lubricants USA Inc., 1500 Valley Road, Wayne, NJ 07470

Telephone: 1,800.462.0835

www.castrol.com/us Email: contactus@bp.com