



Product Data

Tribol™ GR SW 1.5

High Performance Grease for Wind Turbines

Description

Castrol Tribol™ GR SW 1.5 (previously called Optitemp™ SW 1) is a lithium based grease containing a synthetic base fluid and premium extreme pressure (EP) additives. The wax-free nature of the synthetic base oil and the low coefficient of traction (compared with mineral oils), provide excellent low temperature pumpability and very low starting and running torque. It can also offer the potential for energy savings and can reduce operating temperatures in the load zone of rolling and sliding element bearings. The lithium complex thickener gives excellent adhesion, structural stability, sealing effects and water resistance. Primarily intended for a wide variety of applications at extremes of temperature, the grease also has a high level of chemical stability and provides excellent protection against wear, rust and corrosion.

Application

Castrol Tribol GR SW 1.5 is recommended for tough industrial applications especially as encountered in Wind Turbine Main Bearings, Yaw bearings and Pitch bearings. It gives outstanding bearing protection under high loads at low to moderate speeds and in applications where water resistance is critical. Castrol Tribol GR SW 1.5 is also recommended for use in steel and paper mills. Recommended operating temperature range is -40°C to 180°C.

Advantages

- Reduced downtime and maintenance costs because of reduced wear, rust and corrosion.
- Outstanding high and low temperature performance.
- Extended service life with longer intervals between re-lubrication.
- Reduced energy consumption due to low traction coefficient.
- Ability to perform well in the presence of water.

Typical Characteristics

| Name | Method | Units | Tribol GR SW 1.5 |
|---|----------------------|--------------------|------------------|
| Appearance | Visual | - | Homogenous |
| Colour | Visual | - | Beige |
| Consistency | ISO 2137/ASTM D217 | NLGI grade | 1.5 |
| Dropping Point | ISO 2176/ASTM D566 | °C/°F | >260/>500 |
| Base Oil Viscosity @ 40 °C/104 °F | ISO 3104/ASTM D445 | mm ² /s | 460 |
| Base Oil Viscosity @ 100 °C/212 °F | ISO 3104/ASTM D445 | mm ² /s | 46 |
| Water Wash-out at 60 °C/140 °F | ISO 11009/ASTM D1264 | %wt loss | <5 |
| Rust Test - EMCOR (Distilled water) | ISO 11007/ASTM D6138 | Rating | 0/0 |
| Rust Test - EMCOR (1 % NaCl solution) | ISO 11007 modified | Rating | 0/0 |
| Worked Penetration (60 strokes @ 25 °C/77 °F) | ISO 2137/ASTM D217 | 0.1 mm | 290 - 320 |
| Four Ball Weld Load test - Weld Point | ISO 11008/ASTM D2596 | kgf | 315 |
| Four Ball Wear test - Wear Scar Diameter (40 kgf/60 °C) | DIN 51350/ASTM D2266 | mm | 0.4 |
| Four Ball Wear test - Weld Load | DIN 51350 T4 | N | 2800 |

Subject to usual manufacturing tolerances.

This product was previously called Optitemp SW 1. The name was changed in 2015.

Tribol™ GR SW 1.5

10 Apr 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

<http://msdspds.castrol.com>