

Hyspin AWS 37

Anti-wear hydraulic oil

Description

Castrol Hyspin AWS 37 hydraulic oil is based upon highly refined mineral oil enhanced with a stabilised zinc additive system.

Application

Hyspin AWS 37 has been specially formulated to provide good anti-wear and thermal stability performance using proven additive technology. The careful blend of additives with a high quality base stock ensures that Hyspin AWS 37 has excellent hydrolytic and oxidative stability while exhibiting a minimal tendency to produce sludge and deposits. In addition, Hyspin AWS 37 provides corrosion protection to ferrous and yellow metal components found within a hydraulic system. This is designed for use in industrial hydraulic systems which require antiwear protection such as lightly loaded gears, variable speed units and bearings. Hyspin AWS 37 is compatible with the most commonly used nitrile, silicone and fluropolymer seal materials.

Hyspin AWS is classified as follows:

DIN 51502 classification - HLP ISO 6743/4 - Hydraulic Oils Type HM

Hyspin AWS 37 meets the performance requirements of:

DIN 51524 Part 2

Denison (Parker Hannafin) HF-0

AIST (US Steel) 126 & 127

Eaton (formerly Vickers) I-286-S & M-2950-S

Advantages

Hyspin AWS 37 has the following advantages when compared to conventional hydraulic oils:-

- Good thermal and oxidative stability. Oxidative stability reduces deposit formation, resulting in a cleaner system. This can extend the machinery's operating life.
- Excellent anti-wear performance increases wear protection, which can help reduce downtime caused by unscheduled maintenance.
- Good filterability characteristics, including in the presence of water, enables cost savings to be made from increased filter life and reduced maintenance.
- Excellent water separation and hydrolytic stability, measured by industry standard testing. This increases equipment reliability, helping to prolong the lubricant's life and reduce downtime.

Typical Characteristics

Name	Method	Units	Hyspin AWS 37
Density @ 15°C / 59°F	ISO 12185 / ASTM D4052	kg/m ³	877
Kinematic Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm ² /s	37.1
Kinematic Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm ² /s	6.0
Viscosity Index	ISO 2909 / ASTM D2270	-	103
Pour Point	ISO 3016 / ASTM D97	°C/°F	-24/-11
Foam Sequence I - tendency / stability	ISO 6247 / ASTM D892	ml/ml	0/0
Flash Point - open cup method	ISO 2592 / ASTM D92	°C/°F	228/442
Water Separation @ 54°C / 129°F (40/37/3)	ISO 6614 / ASTM D1401	min	10
Air Release @ 50°C / 122°F	ISO 9120 / ASTM D3427	min	4
Copper corrosion (3 hrs@100°C/212°F)	ISO 2160 / ASTM D130	Rating	1a
Rust test - distilled water (24 hrs)	ISO 7120 / ASTM D665A	Rating	Pass
Rust test - synthetic seawater (24 hrs)	ISO 7120 / ASTM D665B	Rating	Pass
FZG Gear Scuffing test - A/8.3/90	ISO 14635-1	Failure Load Stage	12

Subject to usual manufacturing tolerances.

Hyspin AWS 37

20 Nov 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

<http://msdspds.castrol.com>