

Castrol Braycote 194

Corrosion Preventive Compound Solvent Cutback
Cold Application, Transparent, Non-Tacky Film

Description

Castrol Braycote™ 194 is a dark brown, liquid corrosion preventive compound intended for indoor exposure. It is a solvent cutback material designed for cold application, and dries in approximately two hours, leaving a firm, amber, transparent film that will not flow below 175°F (80°C).

Application

Braycote 194 is designed to protect unpainted metal surfaces from the effects of indoor or shed exposure for periods up to one year. It is non-corrosive and readily wets the surfaces of commonly used metals, leaving a continuous film after evaporation of the solvent. This product may be applied by spray, dip or brush. A gallon will cover approximately 300 to 1,600 square feet, leaving a film 1 to 4 mils thick, depending upon method of application and surface geometry. Optimal performance can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. It is recommended that the metal substrate and ambient temperature be 50-95°F (10-35°C) at the time of product application.

Typical Characteristics

Test	Method	Units	MIL-PRF-16173E CLASS I, GRADE 4 REQUIREMENTS	Result
Film Characteristics Transparency	Spec 4.6.11.7	Pass/Fail	Continuous and no cracks Pass	Pass
Nonvolatile Content	Spec 4.6.5.1	%	54.0 - 60.0	55.3
Solvent Distillation Endpoint	Spec 4.6.1 ASTM D86	°C/°F	212/410 Maximum	Pass
Sprayability @4°C/40°F, 35 psig	Spec 4.6.7	gm/sec Report	1.0 Minimum Continuous	10.8 Pass
Flow rate				
Quality of Coverage				
Corrosion, 7 days @55°C/130°F, Wt Change	Spec 4.6.8	mg/cm ²	±1.0 Maximum ±5.0 Maximum ±7.5 Maximum ±0.5 Maximum ±0.2 Maximum ±0.2 Maximum	-0.108 -1.473 -1.424 -0.023 -0.003 -0.007
Brass				
Cadmium				
Zinc				
Magnesium				
Aluminum				
Steel				
Sulfated Residue	ASTM D874	%	3.96 - 4.82	4.48
Flash Point, PMCC	ASTM D93	°C/°F	38/100 Minimum	41/106
Removability	Spec 4.6.10.1	Pass/Fail	Pass	Pass
Film Thickness	Spec 4.6.11.2	Mils	2.0 Maximum	1
Humidity Cabinet	Spec 4.6.11.3	days	30 Days Minimum	Pass (30+)
Salt Spray, Days	Spec 4.6.11.4	days	14 Days Minimum	Pass (17+)
Flow Point, 4 Hrs @80°C/175°F	Spec 4.6.15	Pass/Fail	Pass	Pass
Low Temperature Adhesion	Spec 4.6.12	Pass/Fail	No Flaking	Pass
Pour Point	ASTM D97	°C/°F	Report	-18/0
Film Drying and Tackiness	Spec 4.6.13	Pass/Fail	Pass	Pass
Volatile Organic Content	Spec 4.6.5.2	Report	> 2.8 lbs/gal	3.24
Stability	Spec 4.6.6	Pass/Fail	Pass	Pass

Subject to usual manufacturing tolerances.

Additional Information

Removal

Braycote 194 can be removed from exposed surfaces by vapor degreasing, hot caustic, steam, or petroleum solvents.

Specification

Braycote 194 meets the requirements of and is qualified to MIL-PRF-16173E, Class I, Grade 4.

Castrol, Braycote, and the Castrol logo are trademarks of Castrol Limited, used under licence

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Limited, Pipers Way, Swindon, Wiltshire SN3 1RE, UK
www.castrol.com/industrial