



Techniclean S 20

Aqueous mild alkaline process cleaner

Description

Castrol Techniclean™ S 20 is an aqueous, low alkalinity, industrial process cleaner containing biodegradable surfactants and corrosion inhibitors. The product is free of strong complexing agents.

Application

Techniclean S 20 is designed for inter-operational and final process cleaning operations of ferrous and aluminium goods, suitable for use in a wide range of modern spray and intensive flood wash cleaning equipment. Techniclean S 20 effectively removes residues from parts and components after machining with soluble oils, light duty neat cutting or forming oils as well as thin corrosion preventive films, lubrication oils, swarf and general dirt.

Conditions of Use

Optimum conditions of use are depending on the detailed application requirements and the amount and nature of the soil being removed.

Advantages

- Excellent demulsifying properties provide easy skimming and long bath life – reduces maintenance and disposal cost
- Leaves an ultra-thin temporary corrosion preventive film on the metal surface after drying – minimizes scrap rate which improves productivity
- Low foaming across a wide temperature range and multi-metal compatibility – versatile, enables possible product consolidation

Typical Physical Characteristics

	Test Method	Unit	Value
Appearance	Visual	-	Clear, light yellow liquid
Density @ 15°C	ASTM D 4052	kg/m ³	1033
pH (5% in DI-water)	ASTM E 70	-	9.9
Corrosion test (2% in water, 4° dH)	DIN 51 360 /2	-	0

Recommended Concentrations

Concentration Range (low pressure spray, flood wash):	1 - 4%
Concentration Range (high pressure spray):	1 - 1,5%
Temperature Range:	ambient - 70°C
Spray Pressure:	up to 300 bar
Water Hardness Range:	up to 10 °dH

Techniclean S 20

13 Oct 2017

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol (UK) Limited, PO BOX 352, Chertsey Road, Sunbury On Thames, Middlesex, TW16 9AW
Orders/Enquiries: 0345 9645111 Technical Enquiries: 0345 082 1719
www.castrol.com/industrial