

## Hysol MB 10 BF

Semi-synthetic metalworking fluid

### Description

Castrol Hysol™ MB 10 BF is a semi synthetic metalworking fluid which is chlorine, formaldehyde releasing agent and boron free. It contains an additive package that works in synergy to capture machining performance and surface finish, provide excellent product stability and lower the overall operations costs.

Hysol MB 10 BF is suitable for large central systems and single sump machines.

### Application

Hysol MB 10 BF is especially designed for machining of cast iron and grinding of low-medium alloyed steel.

ü ü suggested core application ü possible application, please consult Castrol representative prior to use

	Cast Iron	Low-medium alloyed steel	High alloyed - stainless steel	Aluminium alloys	Magnesium alloys	Yellow metals
Grinding	ü ü	ü ü	ü	ü		
Milling, Turning (general machining)	ü ü	ü ü	ü	ü		
Drilling	ü ü		ü	ü		
Reaming, Tapping						
Broaching						

### Advantages

- Formaldehyde releasing agent free to comply with health and safety regulations
- Boron, chlorine and nitrite free to fulfill your local legislation, waste treatment and environmental requirements
- Extend fluid life and reduce maintenance and machine downtime
- Low foam in recommended water conditions
- Excellent anti-corrosion properties to protect machine tools and parts
- Excellent wetting properties reduce coolant drag out and deliver clean machine tools and components
- Stable fluid suitable for a wide range of water conditions

## Typical Characteristics

	Test Method	Unit	Value
<b>Concentrate</b>			
Appearance	Visual		Yellow-Amber
Mineral oil content	Calculated	Wt%	13
<b>Emulsion</b>			
Appearance	Visual		Translucent
pH (3%)	DIN 51369 ASTM E70-97		9.8
Refractometer Factor			2.0

Subject to usual manufacturing tolerances.

## Recommended Concentrations

Grinding 5-6%  
General Machining 6-10%

Water range 100-800 ppm CaCO<sub>3</sub>

## Additional Information

	Boron	Formaldehyde releasing agent	EP-Ester	Amines	Chlorine
Additives				ü	

## Storage

To avoid product deterioration always keep the container/drum tightly sealed. Store the product in a cool, dry place away from direct sunlight. Prevent exposure to frost and avoid water ingress. For optimum product stability, it is preferable to store the product indoors between 5°C and 45 °C / 41°F and 113°F.

For more details, please refer the product safety data sheet.

Hysol MB 10 BF

22 Jul 2016

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

<http://msdspds.castrol.com>