



Product Data

## Molub-Alloy™ CH 22 Spray

Multi-service Chain Lubricant

### Description

Castrol Molub-Alloy™ CH 22 Spray (previously called Molub-Alloy™ Chain Oil 22 Spray) is a multi-service chain lubricant designed for use in a variety of plant-wide chain applications. These lubricants are manufactured from a combination of the highest quality components together with an anti-wear/extreme pressure additive system including advanced Molub-Alloy lubricating solids. This product is also formulated to inhibit oxidation and to protect against rust and corrosion.

### Application

Molub-Alloy CH 22 Spray is an excellent lubricant for wire ropes, especially those with a sisal or polypropylene core. It is highly inhibited to protect against rust and corrosion to protect the rope from within.

Molub-Alloy CH 22 without the propellant can be used on conveyors and chains operating at temperatures up to 90°C/190°F. It can be used intermittently at higher temperatures up to 150°C/300°F but more frequent re-lubrication may be required under these conditions. **Application of Molub-Alloy CH 22 Spray contains propellant so care must be taken when applied.**

### Advantages

- Resists accumulation of contamination and abrasive matter: The semi-dry lubrication properties provides a very light oil film, giving the appearance of a dry film. This ensures minimum pickup of abrasive dusts, lint, sand, and other particles, eliminating the formation of abrasive compounds which can increase wear and shorten chain life
- Excellent EP and anti-wear protection under boundary conditions: The compounded Molub-Alloy solids provide superior protection during frequent start-up, slow speeds, and when high and/or shock loads are encountered.
- Superior friction reduction: Promote reduced energy consumption during cold start-up and overall cost savings due to less downtime, more efficient operation, longer parts life and extended lubrication intervals.

## Typical Characteristics

Name	Method	Units	Molub-Alloy CH 22 Spray
ISO Viscosity Grade	-	-	22
Density @ 15°C / 59°F	ASTM D4052 / ISO 12185	kg/m <sup>3</sup>	891
Kinematic Viscosity @ 20°C / 68°F	ASTM D445 / ISO 3104	mm <sup>2</sup> /s	59
Kinematic Viscosity @ 40°C / 104°F	ASTM D445 / ISO 3104	mm <sup>2</sup> /s	22
Kinematic Viscosity @ 100°C / 212°F	ASTM D445 / ISO 3104	mm <sup>2</sup> /s	3.9
Flash Point - open cup method	ASTM D92 / ISO 2592	°C/°F	185 / 365
Pour Point	ASTM D97 / ISO 3016	°C/°F	-45 / -49
Rust test - distilled water (24 hrs)	ASTM D665A / ISO 7120	-	Pass
Rust test - synthetic seawater (24 hrs)	ASTM D665B / ISO 7120	-	Pass
Carbon residue - Conradson test	ASTM D189 / ISO 6615	% w t	0.02
Four Ball Wear test - Wear Scar Diameter (40 kgf / 75°C / 1200 rpm / 1 hr)	ASTM D2266	mm	0.5
Four Ball Wear test - Wear Scar Diameter (300N / 1 hr)	DIN 51350-3B	mm	0.4

Subject to usual manufacturing tolerances.

## Additional Information

**Note: Properties shown are without the Propane/Butane propellant.**

**This product was previously called Molub-Alloy Chain Oil 22 Spray. The name was changed in 2015.**

Molub-Alloy™ CH 22 Spray

14 Mar 2019

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol (UK) Limited, PO BOX 352, Chertsey Road, Sunbury On Thames, Middlesex, TW16 9AW  
 Orders/Enquiries: 0345 9645111 Technical Enquiries: 0345 082 1719  
[www.castrol.com/industrial](http://www.castrol.com/industrial)