

Spheerol EPLX 460

Bearing grease

Description

Spheerol EPLX 460 (previously called Spheerol EPLX) are lithium complex based products containing highly refined mineral oils and fortified with extreme pressure (EP) additives as well as corrosion and oxidation inhibitors.

These greases have been formulated with additives that provide good film strength under medium to high loads.

Application

Spheerol EPLX 460 are general purpose greases designed for plant wide lubrication. These greases provide exceptional film strength and are formulated with a proprietary additive system to protect against friction and wear under heavy loading.

These greases also provide good protection against rust and corrosion as well as resistance to water wash-out; which makes them particularly suitable for equipment where moist or wet conditions are common.

Typical applications are ball and roller bearings, bushings, in steel mills, mining, logging, chemical and construction industries, and where conditions require sealing against outside contaminants such as dust and water.

Advantages

- High mechanical stability – the grease keeps its consistency in service ensuring long lubricant life.
- Good adhesion – continuous lubrication and reduced consumption as film stays between lubricated surfaces.
- Good water resistance – the grease film remains on the surface even in the presence of water.
- Resistant to copper and steel corrosion – helps prevent rust and oxidation on metal surfaces.
- Excellent EP and anti-wear properties – protects equipment against extreme loading and helps minimise bearing component wear.

Additional Information

In order to minimise potential incompatibilities when converting to a new grease, all previous lubricant should be removed as much as possible prior to operation. During initial operation, relubrication intervals should be monitored closely to ensure all previous lubricant is purged.

Typical Characteristics

Name	Method	Units	EPLX 460-1	EPLX 460-2
Appearance	Visual	-	Dark Brown	Dark Brown
Thickener type	-	-	Lithium complex	Lithium complex
Base oil	-	-	Mineral oil	Mineral oil
Consistency	ASTM D217	NLGI Grade	1	2
Density @ 20°C	ASTM D4052	kg/m ³	880	890
Worked Penetration(60 strokes @ 25°C)	ASTM D217	0.1 mm	310-340	265-295
Worked Penetration (100,000 strokes @ 25°C) - change from 60 strokes	ASTM D217	% change	5	3
Dropping point	ASTM D566	°C	260	260
Base Oil Viscosity @ 40°C	ASTM D445	mm ² /s	460	460
Rust Test (distilled water)	ASTM D665A	Pass	Pass	Pass
Copper Corrosion (24 hrs,100°C)	ASTM 4048	Rating	1b	1b
Four Ball Wear test - Wear Scar Diameter (40 kgf /75°C/ 1200 rpm / 1 hr)	ASTM D2266	mm	0.5	0.5
Four Ball Weld Load	ASTM D2596	kg	315	315
Water Wash-out @ 79°C	ASTM D1264	%wt loss	6	5
Oxidation Stability, psi drop, max (99°C, 100 hrs)	ASTM D942	psi	8	7
Dry Roll Stability	ASTM D1831	% change	5	3
Oil Separation (24 hrs, 0.25 psi, 25°C)	ASTM D1742	%	2	1.8
ISO Classification	ISO 6743/9	-	L-XBDFB 1	L-XBDFB 2

The above figures are typical of those obtained with normal production tolerance and do not constitute a specification.

Storage

All packages should be stored upright in a covered area, away from extreme climatic influences, dirt and dust.

Castrol Spheerol EPLX 460

This product was previously called Spheerol EPLX. The name was changed in 2015

22 May 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.